



Dry Concrete Series

DRYCON 730

**Grade 30 Strength
Prepacked Concrete**

A + B Drymix Solution

A + B prepacked high grade dry-mixed concrete solution. 30 MPa in 28 Days.

Uses

- Flooring up to 100 mm
- Concrete for household use, such as table top or stove top.

Benefits

- Shrinkage compensated to prevent cracks
- Can applied as 100 mm flooring in one coat
- High compressive strength
- Easy to mix, only need to add water
- 2 parts system, no need to prepare cement, sand and aggregate

Complied Standard

| EN 998 | EN 1015 |

www.starkendrymix.com.my

Dry Concrete Series

DRYCON 730

**Grade 30 Strength
Prepacked Concrete**

A + B
Drymix Solution



TECHNICAL PROPERTIES

Compressive Strength	> 30 N/mm ²
Dry Shrinkage	< 1.5 mm/m
Abrasion Resistance	Good

PHYSICAL FEATURES

Package	Part A: 40 kg Drymix Powder Part B: 20 kg Aggregate
Water Demand	6.4 - 8ℓ (16 - 20%) to Part A
Yield	25 - 26ℓ Wet Concrete
Binder	Cement, Green Binder
Aggregate Size	10 mm
Application Thickness	11 - 13 m²/ℓ
Pot Life	1 hour

APPLICATION

SUBSTRATE PREPARATION

- 1 Prepare formwork
- 2 For flooring, floor should be free of dust and contaminant. Apply **Bond Buddy 168** as priming coat on smooth or old concrete

MATERIAL PREPARATION

- 1 Mix 1 bag of 40 kg **DRYCON 730** Part A with 6.4 – 8 L water for at least 3 minutes by electrical mixer until homogeneous consistency
- 2 Add 20 kg **DRYCON 730** Part B, mix completely to obtain ready-to-use concrete
- 3 Fill up formwork and trowel smooth
- 4 Apply up to 100 mm thickness in one coat for flooring
- 5 After 7 days, the concrete is ready to receive tiling

RECOMMENDATION

Mix Part A with water to homogenous slurry, then add Part B for slightly mixing.

STORAGE

Shelf life is 6 months if stored in dry and cool place. Avoid direct sunlight exposure.

CURING

Recommended to apply water curing or cover by wet hessian at first 2 days.

Starken Drymix Solutions Sdn. Bhd. (916505-X)

A-1-3A, Pusat Perdagangan Kuchai,
No.2, Jalan 1/127, Off Jalan Kuchai Lama,
58200 Kuala Lumpur, Malaysia.

T: +603-7982 8066 F: +603-7983 8066